

Application No.: 09/833452  
Docket No.: AD6728USNA

Page 3

### CLAIMS

1. (Currently Amended) A multilayer film or sheet comprising:
  - a.) a first co-extruded polymeric layer consisting essentially of ionomer; and
  - b.) a second co-extruded polymeric layer consisting essentially of a polymer selected from the group consisting of ionomer, ~~ionomer-polyethylene blend~~, and ionomer-polyamide blend wherein the second co-extruded layer is in contact with said first co-extruded polymeric layer, wherein the first co-extruded polymeric layer is top of surface layer, the ionomer is present in said ionomer-polyethylene blend in an amount of about 30 weight %; and at least one of said first or second co-extruded polymeric layers ~~contain~~ contains pigments, dyes, flakes, or mixtures thereof.
2. (Canceled)
3. (Previously Presented) A multilayer film or sheet of Claim 1 wherein said ionomer consists essentially of a copolymer derived from ethylene and  $\alpha$ ,  $\beta$ -ethenically unsaturated C<sub>3</sub> to C<sub>8</sub> carboxylic acid wherein said copolymer is partially neutralized with metal ions.
4. (Withdrawn) A multilayer film or sheet of Claim 1 wherein said ionomer-polyamide blend consists essentially of one or more polyamide which forms a continuous phase or co-continuous phase with one or more ionomer dispersed therein, said ionomer is present in the range from 60 to 40 weight percent and said polyamide is present in the range from 40 to 60 weight percent based on the total weight of ionomer and polyamide, said ionomer consisting essentially of a copolymer derived from ethylene and  $\alpha$ ,  $\beta$ -ethenically unsaturated C<sub>3</sub> to C<sub>8</sub> carboxylic acid wherein said copolymer is partially neutralized with metal ions; wherein the average acid content of copolymer prior to neutralization is present in a sufficiently high percentage such that neutralization in the range of 55 to 100 mole percent of the acid present at melt temperature with one or more metal cations increases the viscosity of the ionomer above that of the polyamide.
5. (Canceled)
6. (Previously Presented) A multilayer film or sheet of Claim 1 wherein said first co-extruded polymeric layer is clear and said second co-extruded polymeric layer contains pigments, dyes, flakes, or mixtures thereof.
7. (Withdrawn) A multilayer film or sheet comprising:
  - a.) a first co-extruded polymeric layer consisting essentially of ionomer;

Application No.: 09/833452  
Docket No.: AD6728USNA

Page 4

b.) a second co-extruded polymeric layer consisting essentially of very low density polyethylene in contact with said first co-extruded polymeric layer, wherein at least one of said first or second co-extruded polymeric layers contain pigments, dyes, flakes, or mixtures thereof; and

c.) at least one additional third co-extruded polymeric layer in contact with said second co-extruded polymeric layer.

8. (Canceled)

9. (Withdrawn) A multilayer film or sheet of Claim 7 wherein said ionomer consisting essentially of a copolymer derived from ethylene and  $\alpha$ ,  $\beta$ -ethenically unsaturated  $C_3$  to  $C_8$  carboxylic acid wherein said copolymer is partially neutralized with metal ions.

10. (Canceled)

11. (Withdrawn) A multilayer film or sheet of Claim 7 wherein said first co-extruded polymeric layer is clear and said second co-extruded polymeric layer contains pigments, dyes, flakes, or mixtures thereof.

12. (Withdrawn) A multilayer film or sheet comprising:

a.) a first co-extruded polymeric layer consisting essentially of ionomer;

b.) a second co-extruded polymeric sheet layer consisting essentially of ethylene polar copolymer in contact with said first co-extruded polymeric layer, wherein at least one of said first or second co-extruded polymeric layers contain pigments, dyes, flakes, or mixtures thereof; and

c.) at least one additional third co-extruded polymeric layer in contact with said second co-extruded polymeric layer.

13. (Canceled)

14. (Withdrawn) A multilayer film or sheet of Claim 12 wherein said ionomer consisting essentially of a copolymer derived from ethylene and  $\alpha$ ,  $\beta$ -ethenically unsaturated  $C_3$  to  $C_8$  carboxylic acid wherein said copolymer is partially neutralized with metal ions.

15. (Canceled)

16. (Withdrawn) A multilayer film or sheet of Claim 12 wherein said first co-extruded polymeric layer is clear and said second co-extruded polymeric layer contains pigments, dyes, flakes, or mixtures thereof.

17. (Withdrawn) A multilayer film or sheet comprising:

Application No.: 09/833452  
Docket No.: AD6728USNA

Page 5

- a.) a first co-extruded polymeric layer consisting essentially of ionomer;
- b.) a second co-extruded polymeric sheet layer consisting essentially of ethylene polar copolymer in contact with said first co-extruded polymeric layer, wherein at least one of said first or second co-extruded polymeric layers contain pigments, dyes, flakes, or mixtures thereof; and
- c.) at least one additional third co-extruded polymeric layer in contact with said second co-extruded polymeric layer.

18. (Withdrawn) A multilayer film or sheet of Claim 17 wherein said ionomer-polyamide blend consists essentially of one or more polyamide which forms a continuous phase or co-continuous phase with one or more ionomer dispersed therein, said ionomer is present in the range from 60 to 40 weight percent and said polyamide is present in the range from 40 to 60 weight percent based on the total weight of ionomer and polyamide, said ionomer consisting essentially of a copolymer derived from ethylene and  $\alpha$ ,  $\beta$ -ethenically unsaturated  $C_3$  to  $C_8$  carboxylic acid wherein said copolymer is partially neutralized with metal ions; wherein the average acid content of copolymer prior to neutralization is present in a sufficiently high percentage such that neutralization in the range of 55 to 100 mole percent of the acid present at melt temperature with one or more metal cations increases the viscosity of the ionomer above that of the polyamide.

19. (Canceled)

20. (Withdrawn) A multilayer film or sheet of Claim 17 or 18 wherein said first co-extruded polymeric layer contains pigments, dyes, flakes, or mixtures thereof.

21. (Withdrawn) A multilayer film or sheet of Claim 17 or 18 wherein said second co-extruded polymeric layer is selected from the group consisting of ionomer, ionomer-polyethylene blend, ionomer-polyamide blend, very low density polyethylene, ethylene polar copolymer, and blends thereof.

22-42. (Cancelled)

43. (Previously presented) An article comprising a substrate to which a multilayer film or sheet is adhered, wherein said multilayer film or sheet is the same as recited in claim 1, 3, 6, 54, 55, 56, 57, 58, 59, 60, 61, 64, 65, 66, 67, 71, 72, 73, 75, 76, 77, 78, 79, 80, 81, or 82.

44. (Canceled)

Application No.: 09/833452  
Docket No.: AD6728USNA

Page 6

45. (Withdrawn) An article consisting essentially of a substrate to which a multilayer film or sheet is adhered, wherein said multilayer film or sheet comprises:

- a.) a first co-extruded polymeric layer consisting essentially of ionomer;
- b.) a second co-extruded polymeric layer consisting essentially of very low density polyethylene in contact with said first co-extruded polymeric layer, wherein at least one of said first or second co-extruded polymeric layers contain pigments, dyes, flakes, or mixtures thereof; and
- c.) at least one additional third co-extruded polymeric layer in contact with said second co-extruded polymeric layer.

46. (Canceled)

47. (Withdrawn) An article consisting essentially of a substrate to which a multilayer film or sheet is adhered, wherein said multilayer film or sheet comprises:

- a.) a first co-extruded polymeric layer consisting essentially of ionomer;
- b.) a second co-extruded polymeric sheet layer consisting essentially of ethylene polar copolymer in contact with said first co-extruded polymeric layer, wherein at least one of said first or second co-extruded polymeric layers contain pigments, dyes, flakes, or mixtures thereof; and
- c.) at least one third additional co-extruded polymeric layer in contact with said second co-extruded polymeric layer.

48. (Canceled)

49. (Withdrawn) An article consisting essentially of a substrate to which a multilayer film or sheet is adhered, wherein said multilayer film or sheet comprises:

- a.) a first co-extrusion polymeric layer consisting essentially of ionomer-polyamide blend;
- b.) a second co-extruded polymeric layer in contact with said first co-extrude polymeric layer, wherein at least one of said first or second co-extruded polymeric layers contain pigments, dyes, flakes, or mixtures thereof; and
- c.) at least one additional third co-extruded polymeric layer in contact with said second co-extruded polymeric layer.

50-53. (Canceled)

54. (Previously presented) The multilayer film or sheet of claim 3 further comprising a third co-extruded polymeric layer in contact with said second co-extruded polymeric layer.

Application No.: 09/833452  
Docket No.: AD6728USNA

Page 7

55. (Previously presented) The multilayer film or sheet of claim 6 further comprising a third co-extruded polymeric layer in contact with said second co-extruded polymeric layer.
56. (Previously presented) The multilayer film or sheet of claim 3 wherein the thickness of the multilayer film or sheet is about 1 to about 60 mils or about 8 to about 60 mils.
57. (Previously presented) The multilayer film or sheet of claim 6 wherein the thickness of the multilayer film or sheet is about 1 to about 60 mils or about 8 to about 60 mils.
58. (Previously presented) The multilayer film or sheet of claim 54 wherein the thickness of the multilayer film or sheet is about 1 to about 60 mils or about 8 to about 60 mils.
59. (Previously presented) The multilayer film or sheet of claim 55 wherein the thickness of the multilayer film or sheet is about 1 to about 60 mils or about 8 to about 60 mils.
60. (Previously presented) The multilayer film or sheet of claim 3 wherein the thickness of the first co-extruded polymeric layer is about 1 to about 50 mils or about 2 to about 20 mils.
61. (Previously presented) The multilayer film or sheet of claim 6 wherein the thickness of the first co-extruded polymeric layer is about 1 to about 50 mils or about 2 to about 20 mils.
62. (Previously presented) The multilayer film or sheet of claim 54 wherein the thickness of the first co-extruded polymeric layer is about 1 to about 50 mils or about 2 to about 20 mils.
63. (Previously presented) The multilayer film or sheet of claim 55 wherein the thickness of the first co-extruded polymeric layer is about 1 to about 50 mils or about 2 to about 20 mils.
64. (Previously presented) The multilayer film or sheet of claim 56 wherein the thickness of the first co-extruded polymeric layer is about 1 to about 50 mils or about 2 to about 20 mils.
65. (Previously presented) The multilayer film or sheet of claim 59 wherein the thickness of the first co-extruded polymeric layer is about 1 to about 50 mils or about 2 to about 20 mils.
66. (Currently amended) The multilayer film or sheet of claim 3 wherein the ionomer flow properties of the ~~ionomer~~ in the first co-extruded polymeric layer and the ionomer, ~~ionomer-polyethylene blend~~, or ionomer-polyamide blend in the second co-extruded polymeric layer have flow properties that are matched ~~thereby allowing to allow~~ the ionomer in the first co-extruded layer and the ionomer, ~~or ionomer-polyethylene blend~~, or ionomer-polyamide blend in the second co-extruded polymeric layer, when co-extruded, flow to the full width of the die.
67. (Currently amended) The multilayer film or sheet of claim 61 wherein the ionomer flow properties of the ~~ionomer~~ in the first co-extruded polymeric layer and the ionomer, ~~ionomer-~~

Application No.: 09/833452  
Docket No.: AD6728USNA

Page 8

~~polyethylene blend~~, or ionomer-polyamide blend in the second co-extruded polymeric layer have flow properties that are matched thereby allowing to allow the ionomer in the first co-extruded layer and the ionomer, ~~or ionomer-polyethylene blend~~, or ionomer-polyamide blend in the second co-extruded polymeric layer, when co-extruded, flow to the full width of the die.

68. (Currently amended) The multilayer film or sheet of claim 65 wherein the ionomer flow properties of the ionomer in the first co-extruded polymeric layer and the ionomer, ~~ionomer-polyethylene blend~~, or ionomer-polyamide blend in the second co-extruded polymeric layer have flow properties that are matched thereby allowing to allow the ionomer in the first co-extruded layer and the ionomer, ~~or ionomer-polyethylene blend~~, or ionomer-polyamide blend in the second co-extruded polymeric layer, when co-extruded, flow to the full width of the die.

69. (Currently amended) The multilayer film or sheet of claim 1 wherein the ~~top-layer~~ first co-extruded polymeric layer has a Distinctness of Image (DOI) of at least 80 and a gloss that exceeds 60% at a 20 degree angle.

70. (Currently amended) The multilayer film or sheet of claim 6 wherein the ~~top-layer~~ first co-extruded polymeric layer has a Distinctness of Image (DOI) of at least 80 and a gloss that exceeds 60% at a 20 degree angle.

71. (Currently amended) The multilayer film or sheet of claim 67 wherein the ~~top-layer~~ first co-extruded polymeric layer has a Distinctness of Image (DOI) of at least 80 and a gloss that exceeds 60% at a 20 degree angle.

72. (Currently amended) The multilayer film or sheet of claim 68 wherein the ~~top-layer~~ first co-extruded polymeric layer has a Distinctness of Image (DOI) of at least 80 and a gloss that exceeds 60% at a 20 degree angle.

73. (Previously presented) The multilayer film or sheet of claim 1 wherein the second co-extruded polymeric layer is an ionomer.

74. (Previously presented) The multilayer film or sheet of claim 6 wherein the second co-extruded polymeric layer is an ionomer.

75. (Previously presented) The multilayer film or sheet of claim 54 wherein the second co-extruded polymeric layer is an ionomer.

76. (Previously presented) The multilayer film or sheet of claim 55 wherein the second co-extruded polymeric layer is an ionomer.



Application No.: 09/833452  
Docket No.: AD6728USNA

Page 9

77. (Previously presented) The multilayer film or sheet of claim 56 wherein the second co-extruded polymeric layer is an ionomer.
78. (Previously presented) The multilayer film or sheet of claim 63 wherein the second co-extruded polymeric layer is an ionomer.
79. (Previously presented) The multilayer film or sheet of claim 65 wherein the second co-extruded polymeric layer is an ionomer.
80. (Previously presented) The multilayer film or sheet of claim 72 wherein the second co-extruded polymeric layer is an ionomer.
81. (Previously presented) The multilayer film or sheet of claim 3 wherein the second co-extruded polymeric layer is the ionomer-polyamide blend.
82. (Previously presented) The multilayer film or sheet of claim 3 wherein the second co-extruded polymeric layer is the ionomer-polyethylene blend.
83. (Previously presented) The article of claim 43 wherein the substrate is metal, polymer, or polymer composite.
84. (Previously presented) The article of claim 83 wherein the substrate is metal, polymer, or polymer composite and the substrate optionally has a printed design or pattern and said multilayer film or sheet is clear.